

East Dune Trading (Pty) Ltd T/A



51 Gerhardus Street, Strijdom Park, South Africa
P.O.Box 912 North Riding 2160 South Africa
Tel: 011 466 8250/1/2 Fax: 086 697 7796 Email:
info@waterhouse.co.za
Reg.No. 2008/010619/07 VAT No: 4200247635

PVC Industrial Tubing

Made in South Africa

REINFORCED (CR)				
ID	BURST PRESSURE	WORKING PRESSURE	WALL THICKNESS	WEIGHT PER m
3				
5	56	14	2	
6.5	56	14	2.3	86
8	48	12	2.4	102
10	48	12	2.5	120
12.5	48	12	2.5	150
16	40	10	2.8	210
20	40	10	3.2	305
25	40	10	3.6	490
32	36	9	5.0	720
40	32	8	5.6	1007
50	28	7	7.0	1667
mm	BAR	BAR	wall mm	grams

UN-REINFORCED		
ID	THIN UR1	THICK UR2
3	0.8	1.4
5	0.8	1.4
6.5	1.1	2.2
8	1.1	2.2
10	1.2	2.7
12.5	1.6	2.7
16		2.8
20		2.8
25		3.3
32		3.3

- Un- reinforced used for Low-pressure applications, conveyance of fluids and chemicals, Fish ponds and aquariums ect.
- Reinforced for medium pressure applications such as air, chemicals fluids ect.
- Temperature range from 0 - 60 degrees Celsius.
- For chemical resistance refer to a pvc resistance chart.
- Measurements are worked on averages and may differ slightly, we reserve the right to change and modify these specifications at any time.